JATMA国内自主規制グレーディング用試験データ提出

申請会社 東洋ゴム工業㈱ 商品名 TRANPATH Ne 提出日 : 平成22年3月19日

サイズ

偏平率	代表	きサイズ		LI/SS	転がり抵抗 係数(RRC)	ク゛レーテ゛ィンク゛
65's	205	65 R	16	95H	8.90	Α
60's	215	60 R	17	96H	8.83	Α

ウェットグ リップ性能 <i>152.7</i>	ク゛レーテ゛ィンク゛
152.7	Ь

偏平率

	単位(N/kN)	
転がり抵抗係数(RRC)	等級	ウェットグリップ性能(G)
RRC≦6.5	AAA	155≦G
6.6≦RRC≦7.7	AA	140≦G≦154
7.8≦RRC≦9.0	Α	125≦G≦139
9.1≦RRC≦10.5	В	110≦G≦124
10.6≦RRC≦12.0	С	

偏平率	+	トイズ 65 R		LI/SS	RRC	ウェット
65's	205	65 R	16	95H	Α	b
60's	215	60 R	17	96H	Α	b
						-
						

		
	1	

LI/SS

RRC

ウェット	偏平率	サイズ	LI/SS	RRC	ウェット

単位 (%)

等級 a

b

С